

# 100 FLEX-EPOXY 100% SOLIDS EPOXY MORTAR & GROUT

## CHEMICAL RESISTANCE CHART

CHEMICAL	PROLONGED EXPOSURE	INTERMITTENT EXPOSURE	NOT RECOMMENDED
5% Acetic Acid		✓	
10% Acetic			✓
Ammonium Hydroxide	✓		
30% Ammonium Chloride	✓		
40% Ammonium Nitrate	✓		
40% Ammonium Sulfate	✓		
Sodium Hypochlorate- 6.5% act C1	✓		
Boric Acid	✓		
Butyl Alcohol		✓	
Calcium Chloride	✓		
Caustic Soda-50%	✓		
Caustic Potash-50%	✓		
10% Citric Acid		✓	
Diesel Fuel	✓		
Formaldehyde		✓	
10% Formic Acid		✓	
Glycerol	✓		
10% Hydrochloric Acid	✓		
30% Hydrogen Peroxide	✓		
Iron Chloride	✓		
Isopropyl Alcohol	✓		
Gasoline	✓		
Methylene Chloride			✓
Mineral Spirits	✓		
10% Nitric Acid		✓	
Olive Oil	✓		
10% Oxalic Acid	✓		
Perchloroethylene		✓	
50% Phosphoric Acid	✓		
Sodium Chloride	✓		
50% Sodium Hydroxide	✓		
10% Sulfuric Acid	✓		
96% Sulfuric Acid			✓
10% Tannic Acid	✓		
Toluene			✓
Trichlorethane			✓
Turpentine	✓		
Xylene			✓