

56 SR

PREMIUM POLYMER-MODIFIED SAG-RESISTANT MORTAR

DESCRIPTION

56 SR is a premium-grade, sag resistant mortar, designed specifically for thin or medium-bed, wall, floor and countertop installation of large format tile and stone. 56 SR provides excellent sag resistance and mortar transfer to backs of larger format tile & stone on vertical applications, as well as superior tile support and mortar transfer on horizontal applications. A premium polymer modified dry set mortar consisting of high performance polymers and water retention additives, carefully graded sands, Portland cement, and special additives, which contribute to the unique characteristics of 56 SR. Available in Grey & White.

BASIC USES

- Installation of large format porcelain, ceramic, mosaic, quarry and paver tiles, or natural stone such as marble, granite, slate and precast terrazzo tile on horizontal surfaces where superior mortar transfer to backs of tile and support for large, heavy tile is required.

RECOMMENDED SURFACES

- Installation over concrete, masonry, approved tile backer boards.
- Installation over cement mortar beds or levelling compounds.
- Existing surfaces of properly prepared ceramic tile, stone, or cement terrazzo.
- Exterior Grade Plywood or Gypsum Board – in interior dry areas only
- Existing surfaces of properly prepared non-cushion sheet vinyl flooring, VCT, or cutback adhesive residue *

* Check with Flextile Ltd. as to acceptability of specific surfaces

LIMITATIONS

Do not use over particleboard, Masonite, chipboard, OSB or similar unstable materials. Do not use directly over cushioned resilient flooring, rubber, plastic, metal, painted surfaces, asphalt, or plywood surfaces in wet areas. Do not use over single layer plywood floors. Use only on surfaces that are maintained at a temperature above 10°C (50°F) and below 35°C (95°F) during application and for at least 72 hours after application. On exterior applications, protect from rain until thoroughly dried and protect from freezing for at least 14 days after installation. Cure for 28 days before water immersion. Consult local building code requirements for use on exterior commercial building facades. For heavy service exterior or water immersion applications, or where extreme freeze/thaw conditions are present, use Flextile 51/44 or Flextile 58XT Fast Set high solids, two-component latex Portland cement mortar systems.

FEATURES

- Excellent for non-sag, thin or medium bed installations of large dimension, heavy textured tile and stone on both vertical or horizontal surfaces.
- Excellent flexibility and bond strength.
- Contributes to LEED certification.
- For interior and exterior floor, wall and countertop installations.
- Easy to use - just mix with water and apply.
- Reduces the need to backbutter large format or heavily lugged tile in order to achieve required mortar transfer to backs of tile.
- Supports large format tile, reducing lippage.
- Excellent workability.

LEED Points Information LEED Points Contribution

Low-emitting materials 1 point

Regional materials* 1 point

* May be eligible

TECHNICAL DATA (at 23°C [73°C] and 50% humidity)

Exceeds ANSI A118.4 and A118.11 specifications.

Description

28 DAY SHEAR STRENGTH	ANSI REQUIREMENT	TYPICAL RESULT
Glazed Wall Tile	> 2.1 MPa (300 psi)	3.85 MPa (550 psi)
Impervious Ceramic Tile (Porcelain)	> 1.4 MPa (200 psi)	2.6 MPa (380 psi)
Quarry Tile	> 1.0 Mpa (150 psi)	3.4 MPa (480 psi)
Quarry Tile / Plywood	> 1.0 Mpa (150 psi)	1.8 MPa (260 psi) (wood failure)

Description

PHYSICAL PROPERTIES

Pot Life	2-3 hours
Open Time	30-40 minutes
Initial Cure	24-48 hours
Final Cure	28 days
Specific Gravity (dry)	1.64
Specific Gravity (wet)	1.85
pH (paste)	approx. 12
Cleanability :	with water before material dries
Shelf Life	1 year from production date when stored in dry, heated conditions

Approx. coverage per 22.7 kg (50 lb) bag:*

6 mm x 10 mm (1/4" x 3/8") - square-notch trowel	- 5.5 M ² (60 ft ²)
10mm x 10 mm (3/8" x 3/8") - square-notch trowel	- 4.1 M ² (45 ft ²)
19 mm x 14 mm (3/4" x 9/16") - round-notch trowel	- 2.8 M ² (30 ft ²)

* Coverages given are for estimating purposes only. Actual coverages may vary depending on job-site conditions and installation techniques used.

INSTALLATION**PREPARATORY WORK**

Surfaces must be sound, even, dry and free of grease, oil, dirt, paint, curing compounds or sealers, or other foreign matter. Surfaces must be true to a tolerance of ± 3 mm (1/8") in 2.4 meters (8 ft.) for walls and 6mm (1/4") in 3 meters (10 ft.) for floors. Concrete surfaces should have a wood float or steel trowel with light broom finish. Roughen smooth concrete surfaces. Plywood floors should be designed for maximum deflection of L/360 of span. This normally requires an overlay of 16 mm (5/8") exterior grade plywood over 25 mm (1") nominal boards or 16 mm (5/8") plywood when on joists 40 cm (16") O.C. Fasten overlay with screw type nails and glue where possible. Leave a 3 mm - 6 mm (1/8"-1/4") gap between sheets of overlay and next to all vertical surfaces to allow for expansion. Refer to current editions of TTMAC 09 30 00 Tile Installation Manual, or TCNA Handbook For Ceramic Tile Installation for information regarding placement of movement or expansion joints, or for further substrate acceptability information.

APPLICATION

Mix with approximately 5.0-5.5 Litres (1.3-1.45 U.S gals) of water per 22.7 kg (50 lb) bag. Avoid using high-speed mixers. Allow mixed mortar to slake for at least 10 minutes, then re-mix without adding further material or water. Spread a thin layer of mixed mortar with flat side of trowel to wet out the substrate; then reapply sufficient material with a suitably notched trowel that will leave enough mortar to give at least 85% (Interior applications) or 95% (Exterior applications) coverage to the backs of tile. It is imperative that an appropriate sized trowel is used in conjunction with larger format tile or stone, so that adequate coverage is achieved. Comb that area which can be covered with tile before skinning occurs. Mortar should be troweled with notches running in straight, parallel lines. Press or beat in tile while moving slightly in the opposite direction of troweled mortar ridges, to achieve maximum coverage. Do not adjust tiles after they have been set for more than 15 minutes.

CURING AND GROUTING

Protect from all traffic and delay grouting until cured at least 24 hours. On applications where job site temperatures are below room temperature, or where impervious tile is being installed on impervious surfaces such as membranes, existing surfaces of ceramic tile, etc, extended curing is recommended to ensure that mortar is sufficiently cured prior to grouting and/or foot traffic. Refer to Flextile Installation Bulletin #8. Grout using Flextile Polymer Modified Grout, Flextile Flex-Epoxy 100-100% Solids Epoxy Grout, or Flextile ColourMax Polyurethane Grout.

CAUTION

Freshly mixed cement, mortar, concrete or grout may cause skin injury. Avoid extended contact with skin where possible and wash exposed skin areas promptly with water. If any cement or cement mixtures get into the eye, rinse immediately and repeatedly with water and get prompt medical attention. Keep out of reach of children.

SAFETY

Refer to Flextile Material Safety Data Sheet for detailed health and safety information.

AVAILABILITY AND COSTS

Flextile 56 SR Premium Polymer Modified Sag-Resistant Mortar is available from Flextile Ltd. and its distributors in 22.7 kg (50 lb) bags. Available in Grey & White formulas.

Cost: Data supplied upon request.

WARRANTY

Flextile warrants that this product is of merchantable quality and is suitable for the purpose for which it is intended. Flextile's liability under this warranty shall be limited to replacement of its product found to be defective or, at its option, a refund of the purchase price.

MAINTENANCE

No maintenance is required except where damages result from unforeseen circumstances. Repair procedures shall be directed by Flextile or its distributors.

TECHNICAL SERVICES

Flextile maintains a well-equipped laboratory able to test its products in conjunction with the products with which they are used. Technical assistance for use of Flextile products is available upon request.

RELATED REFERENCES

Current editions of: Ceramic Tile Installation Manual (09 30 00) from the TTMAC, and TCNA Ceramic Tile Installation Handbook.