

4001 CONCENTRATED - ACRYLIC LATEX PRIMER

BASIC USES

For the preparation of fully cured concrete, exterior grade plywood, cementitious backer units, or other approved tile substrates prior to the application of Flextile Flexilastic 1000 and 2000SC Crack Isolation and Sound Control Membrane Systems.

COMPOSITION AND MATERIALS

A high latex concentrate water-based acrylic latex primer.

LIMITATIONS

For use specifically with Flextile Flexilastic Membrane systems. Not recommended as a primer for Portland cement self leveling products or other leveling or patching products. Do not freeze. Do not apply to surfaces with temperatures below 10°C (50°F) or above 45°C (120°F).

FEATURES

- Excellent adhesion to fully cured concrete and exterior grade plywood surfaces.
- For use on Exterior applications.
- For use on Vertical applications.
- For use on existing floor covering surfaces, or otherwise difficult to bond to substrates.
- Easy to apply.
- Provides a strong bond for Flextile Flexilastic peel & stick membrane systems.
- VOC compliant.

TECHNICAL DATA

Typical Physical Properties

Appearance	Low viscosity, white liquid
Tack Free Time	20 – 45 minutes
Shelf Life	1 year (minimum)
Application Temperature Range	10°C (50°F) to 45°C (120°F)

Approximate coverage per 18.9L (5 US Gallon) unit

Approx. 167 m² (1800 ft²) to 232 m² (2500 ft²), depending on porosity of surface.

- *Coverages given are for estimating purposes only. Actual coverages may vary depending on job site conditions and installation techniques used.*

LIMITATIONS**PREPARATORY WORK**

All surfaces must be clean, even, dry and free of grease, oil, loose paint, curing compounds or sealers, or other foreign matter. Existing concrete surface which have been scarified, ground or sanded must be thoroughly cleaned of dust, loose concrete, etc prior to applying primer. New concrete surfaces should be fully cured, dry, finished to a wood float or light broom finish, and be true to within 6 mm (1/4") in 3 m (10'). Apply a latex modified mortar skim coat to existing surfaces where abrasion cannot provide a porous enough surface, or to uneven surfaces prior to applying 4001 Concentrated Primer.

Ensure that skim coat is sufficiently cured prior to applying Primer.

Interior plywood surfaces should be designed for maximum deflection of 1/360 of span.

This normally requires a 16 mm (5/8") layer of exterior grade plywood over 25 mm (1") boards

or 16 mm (5/8") plywood when on joists 40 cm (16") O/C. Plywood sheets should be fastened with screw type nails and glued where possible. Leave a 3 mm (1/8") gap between top sheets of plywood and next to all vertical surfaces to allow for expansion.

APPLICATION

DO NOT DILUTE PRIMER when applying to Vertical, Exterior, or other difficult to bond to surfaces such as porous concrete or mortar bed surfaces, existing surfaces of tile or stone, etc. Use Flextile 4001 Concentrated Primer at **FULL STRENGTH** for these applications. Mix primer in container just prior to applying. Roll or brush primer onto surface at an approximate rate of 9 m²/L (360 ft²/usg). Allow primer to fully dry prior to installing Flexilastic membranes. Prime only as much area as can be covered with membrane in half a day's work. Re-prime areas not covered in half a day's work with a light coat of 4001 Concentrate Primer.

When fully cured, primer should be tacky to the touch, but will not come off the surface.

SAFETY

Refer to Flextile Material Safety Data Sheet for detailed health and safety information.

AVAILABILITY AND COST

Flexilastic 4001 Concentrated Primer is available from Flextile Limited and listed distributors in 18.9 L (5 USG) container. Cost data is available upon request from Flextile distributors (refer to distributor list @ www.flextile.net).

WARRANTY

Flextile warrants that this product is of merchantable quality and is suitable for the purpose for which it is intended. Flextile's liability under this warranty shall be limited to replacement of its product found to be defective or, at its option, a refund of the purchase price. For extended project warranties for installations using Flextile 4001 Primer, contact Flextile Limited.

MAINTENANCE

No Maintenance is required except where damages result from unforeseen circumstances. Repair procedures shall be directed by Flextile or its distributors.

TECHNICAL SERVICES

Flextile maintains a well-equipped laboratory able to test its products in conjunction with the products with which they are used. Technical assistance for use of Flextile products is available upon request.

RELATED REFERENCES

Current editions of: Ceramic Installation Manual (09 30 00) from the TTMAC, and TCNA Ceramic Tile Installation Manual.

FLEXITILE PRODUCTS COMPLY WITH THE BUY AMERICA PROGRAM AS OUTLINED BY THE UNITED STATES GOVERNMENT, INCLUDING WHEN FEDERAL FUNDS ARE USED.

01/09